

TEST REPORT



Test Report No.RPT/T(A)/25/011887

Dated 2025-08-22



TEST REPORT



Test Report No.RPT/T(A)/25/011887

Dated 2025-08-22

Applicant : SHASHI ENTERPRISES
No. 2,Jothi Venkatachalam Road
Atkinson Palace, Flat 1-A, First Floor
Chennai;Tamil Nadu-600007
India

Attention : Mr. R. Nithish,

Test sample : Received on 2025-08-16 12:52 pm

Test period : 2025-08-18 to 2025-08-22

Sample description : Sample A:INFINISUEDE BT067 in Color : TS06M327 FOSSIL

Fiber Content : SYNTHETIC

Product Type/End use : FOOTWEAR/BAG/GARMENTS

Country of Origin : CHINA

Country of Destination : INDIA

Supplier : DONGGUAN SHIFENG TRADING CO.LTD

Name of buyer/ destination : Self Reference

Note : The submitted Samples were not drawn by laboratory.

Unless otherwise agreed upon, PASS or FAIL verdicts are given based on the measured values without any considerations of measurement uncertainties. Every test method has a measurement uncertainty which has been evaluated by the laboratory and are available on request. By taking measurement uncertainties into account it might happen that measured values can neither be assessed as PASS nor as FAIL

1. The testing conditions are followed as per the reported test standard and the test results are reported in accordance with the relevant standard's reporting guideline. Additional test condition beyond those reported can be obtained by contacting the laboratory.
2. The laboratory will retain the sample(s) for 45 days except for the mandatory retention period specified by the Regulatory Bodies and unless otherwise specified by the client.

By accepting this document the customer hereby agrees and accepts the 'Terms & Conditions' and the relevant 'Testing & Certification Regulations' of TÜV SÜD South Asia Pvt. Ltd. which are available at Company's website at the link <https://www.tuvsud.com/en-in/terms-and-conditions>

Note: The test report is electronically generated. Hence original signature is not required.

Note : (1) The results relate only to the items tested, (2) The test report shall not be reproduced except in full without the written approval of the laboratory, (3) Any use for advertising purposes must be granted in writing. This technical report may only be quoted in full. This report is the result of a single examination of the object in question and is not generally applicable evaluation of the quality of other products in regular production. For further details, please see testing and certification regulation, chapter A-3.4. (4) The correctness of the information related to sample(s) in the Test Request Form/Customer letterhead/Email is the customer's responsibility. The laboratory reports the said information in the test report and is not liable for the same.

Laboratory:
TÜV SÜD South Asia Pvt. Ltd.
S.F.No.139/1B,Ammananthangal
Village,Walajapet,Ranipet,
Tamil Nadu-632513.

Phone :+91 4172 281 300
Fax :+91 4172 281 303
E-Mail :Prabudoss.Boopathy@tuvsud.com
Url :www.tuvsud.in/softlines
Control No. :15362240.180825.002

Regd. Office :
TUV SUD South Asia Pvt. Ltd. Off Saki
Vihar Road, Saki naka, Andheri (East),
Mumbai-400072. India

TEST REPORT



Test Report No.RPT/T(A)/25/011887

Dated 2025-08-22

Result summary / Conclusion :

<u>Test</u>	<u>A</u>
Colorfastness To Perspiration	PASS
Colorfastness to Crocking	PASS

Remarks: "The test method and specifications have been followed as provided by the Applicant".

Authorised By

Berlin Mathews
(Authorised Signatory)

Please contact :

For any technical issues : Sheshadri Rajasekar at Sheshadri.Rajasekar@tuvsud.com

For any complaint : R, Rakesh at Rakesh.R@tuvsud.com.

Laboratory:
TÜV SÜD South Asia Pvt. Ltd.
S.F.No.139/1B,Ammananthangal
Village,Walajapet,Ranipet,
Tamil Nadu-632513.

Phone :+91 4172 281 300
Fax :+91 4172 281 303
E-Mail :Prabudoss.Boopathy@tuvsud.com
Url :www.tuvsud.in/softlines
Control No. :15362240.180825.002

Regd. Office :
TUV SUD South Asia Pvt. Ltd. Off Saki
Vihar Road, Saki naka, Andheri (East),
Mumbai-400072. India

TUV®

Page 3 of 5

TEST REPORT



Test Report No.RPT/T(A)/25/011887

Dated 2025-08-22

Test Results - Accredited Parameters

1.0 Colorfastness to Crocking

Test Method: SATRA TM 167 : 2017, Atmospheric conditions: Temperature: 20.0° ± 2°C;Relative Humidity: 65±5%

Results (GSR)


Customer Spec.

Color Staining	Dry (10 cycles)	4-5
Color Staining	Wet (10 cycles)	4

Min. 4

Min. 3

Note: GSR denotes Grey Scale Rating



TEST REPORT



Test Report No.RPT/T(A)/25/011887

Dated 2025-08-22

Test Results - Non-Accredited Parameters

2.0 Colorfastness To Perspiration

Test Method: AATCC TM15 : 2021,

		Acid	Customer Spec.
Color Change	Base	4.0	Min. 4
Color Staining	Acetate	4.5	
Color Staining	Cotton	4.0	
Color Staining	Nylon	4.0	
Color Staining	Polyester	4.0	
Color Staining	Acrylic	4.5	
Color Staining	Wool	4.5	

Grey scales for staining and color change had been used for Grading

Notes on Colour change & Staining Grade

Grade 5 = Equal

Grade 4 = Slight Change & Staining

Grade 3 = Noticeable Change & Staining

Grade 2 = Considerable Change & Staining

Grade 1 = Much Change & Staining

Tests subcontracted to other accredited TUV SUD laboratory.

- End of Test report-